

IN THE CLAIMS:

The text of all pending claims, (including withdrawn claims) is set forth below. Cancelled and not entered claims are indicated with claim number and status only. The claims as listed below show added text with underlining and deleted text with ~~striketrough~~. When strikethrough cannot easily be perceived, or when five or fewer characters are deleted, [[double brackets]] are used to show the deletion. The status of each claim is indicated with one of (original), (currently amended), (cancelled), (withdrawn), (new), (previously presented), or (not entered). Please AMEND claims 5 and 19 and CANCEL claim 13 without prejudice or disclaimer in accordance with the following:

1. (cancelled)
2. (previously presented) The lithium battery according to claim 5, wherein the liquid lithium metal is coated using a doctor blade.
3. (previously presented) The lithium battery according to claim 5, wherein the liquid lithium metal is coated using a calendering process.
4. (cancelled)
5. (currently amended) A lithium battery comprising:
 - a lithium negative electrode prepared by melting lithium metal under an inert gas atmosphere and coating the liquid lithium metal uniformly on a metal current collector;
 - a positive electrode including a binder;
 - a separator placed between the positive and negative electrodes; and
 - an electrolyte comprising a lithium salt and organic solvents, contained in the positive and negative electrodes and the separator,wherein the current collector is nickel, copper or a metal-sprayed nickel or copper, and the metal being sprayed is a lithium-wetting metal,
wherein the lithium-wetting metal is selected from the group consisting of Al, Si, and Sn,
and

wherein the lithium battery retains 90% or greater of a capacity at a fiftieth charging and discharging cycle as compared to a capacity at a first charging and discharging cycle.

6. (previously presented) The lithium battery according to claim 5, wherein the binder is selected from the group consisting of polyvinylidene fluoride, polytetrafluoroethylene, polyvinyl acetate, polyethylene oxide, polypyrrolidone, and polyvinyl alcohol.

7. (cancelled)

8. (previously presented) The lithium-sulfur battery according to claim 10, wherein the liquid lithium metal is coated using a doctor blade.

9. (previously presented) The lithium-sulfur battery according to claim 10, wherein the liquid lithium metal is coated using a calendaring process.

10. (previously presented) A lithium-sulfur battery comprising:
a lithium negative electrode prepared by melting lithium metal under an inert gas atmosphere and coating the liquid lithium metal on a metal current collector;
a positive electrode comprising a positive active material, an electrically conductive material and a binder, the positive active material comprising at least one sulfur-based material selected from the group consisting of elemental sulfur and solid Li_2S_n ($n \geq 1$) coated on a current collector;
a separator placed between the positive and negative electrodes; and
an electrolyte comprising a lithium salt and organic solvents, contained in the positive and negative electrodes and the separator,
wherein the current collector is nickel, copper or a metal-sprayed nickel or copper, and the metal being sprayed is lithium-wetting metal.

11. (original) The lithium-sulfur battery according to claim 10, wherein the lithium wetting metal is selected from the group consisting of Al, Si, and Sn.

12. (previously presented) The lithium-sulfur battery according to claim 10, wherein the binder is selected from the group consisting of polyvinylidene fluoride, polytetrafluoroethylene, polyvinyl acetate, polyethylene oxide, polypyrrolidone, and, polyvinyl alcohol.

13. (cancelled)

14. (previously presented) The lithium battery according to claim 5, wherein the lithium battery retains 70% or greater of a capacity at the one hundredth charging and discharging cycle as compared to the capacity at the first charging and discharging cycle.

15. (original) The lithium battery according to claim 13, wherein the lithium battery retains 70% or greater of the capacity at the one hundredth charging and discharging cycle as compared to the capacity at the first charging and discharging cycle.

16. (previously presented) The lithium battery according to claim 10, wherein the lithium battery retains 90% or greater of a capacity at the fiftieth charging and discharging cycle as compared to the capacity at the first charging and discharging cycle.

17. (previously presented) The lithium battery according to claim 10, wherein the lithium battery retains 70% or greater of a capacity at the one hundredth charging and discharging cycle as compared to the capacity at the first charging and discharging cycle.

18. (cancelled)

19. (currently amended) A method of manufacturing a lithium battery, comprising:
melting a lithium metal under a gas atmosphere to produce ~~the a~~ liquid lithium metal;
coating the liquid lithium metal on a current collector to create a negative electrode;
obtaining a positive electrode that includes a binder a positive electrode including a binder;
placing a separator between the positive and negative electrodes to produce an assembly; and
soaking an electrolyte into the assembly.

wherein the lithium battery retains 90% or greater of a capacity at a fiftieth charging and discharging cycle as compared to a capacity at a first charging and discharging cycle.

20. (cancelled)